

## Product Description

EL-Pro™ P642J is an impact copolymer polypropylene resin which contains anti-static agent and UV stabilizer. It is suitable for Injection molding process. This resin is recommended for product that requires high stiffness with good impact strength.

## Typical Application

- Automotive parts
- Home appliance parts
- Battery case
- Industrial uses
- Toy, Furniture

## Product Characteristics

- High impact strength
- Good processibility and stiffness
- UV stabilizer and anti-static
- UL Yellow Card
- RoHS

## Physical Properties

| Property                          | Test Method                         | Typical Value | Unit               |
|-----------------------------------|-------------------------------------|---------------|--------------------|
| Melt Flow Rate                    | ASTM D 1238 @ 230°C, 2.16 kg        | 10            | g/10 min           |
| Density                           | ASTM D 1505                         | 0.910         | g/cm <sup>3</sup>  |
| Tensile Strength at Yield         | ASTM D 638 @ Speed 50 mm/min        | 280           | kg/cm <sup>2</sup> |
| Tensile Strength at Break         | ASTM D 638 @ Speed 50 mm/min        | 180           | kg/cm <sup>2</sup> |
| Flexural Modulus                  | ASTM D 790                          | 14,000        | kg/cm <sup>2</sup> |
| Notched Izod Impact               | ASTM D 256 @ 23 °C                  | 98            | J/m                |
| Notched Izod Impact               | ASTM D 256 @ 0 °C                   | 59            | J/m                |
| Notched Izod Impact               | ASTM D 256 @ -20 °C                 | 39            | J/m                |
| Rockwell Hardness                 | ASTM D 785                          | 80            | R-Scale            |
| Melting Point                     | ASTM D 2117                         | 163           | °C                 |
| Heat Deflection Temperature (HDT) | ASTM D 648 @ 4.6 kg/cm <sup>2</sup> | 110           | °C                 |
| % Shrinkage (2mmt) MD             | TPE Method                          | 1.3           | %                  |
| TD                                | TPE Method                          | 1.1           | %                  |
| Flammability                      | UL - 94                             | HB            | -                  |

**Note:** Conversion factor for changing unit from kg/cm<sup>2</sup> to MPa is divided by 10.20

## Processing Techniques

The actual processing conditions depend on each machine type, product size, mold design and environment. Recommended processing conditions:

Melt temperature: 230-270°C  
 Pressure (of Max. Pressure):

Mold temperature: 25-70°C  
 Injection 40-80%

Injection speed: Fast  
 Packing and Holding 30-60%

Screw speed: 40-70 rpm  
 Back 10%

### Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your SCG Chemicals technical service engineer at the address or telephone number as specified below.

## Product Available Form

- Pellet

## Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Sea bulk container

## Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited/ Thai Polypropylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50°C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odor generation and color changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabeled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

## Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Plastics/SCG Performance Chemicals technical service.

## Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Plastics/SCG Performance Chemicals technical service.

## Related Documents

- The latest version of this document will be available at our website, [www.scgchemicals.com](http://www.scgchemicals.com), or can be obtained from the SCG Plastics/SCG Performance Chemicals technical service.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
  - Material Safety Datasheet
  - Statement on compliance to food contact regulations

## Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.